

## END GLOVE WORRIES. RELAX WITH LAVENDER\*.

LAVENDER\* Nitrile Exam Gloves are thinner, lighter, and more economical than standard nitrile, yet they retain the protective properties required for excellent performance across a wide range of healthcare tasks. They're the ideal replacement for vinyl and latex exam gloves, providing a superior barrier and more comfort than vinyl, while avoiding the problem of latex allergy, all at an affordable price.

### NITRILE GLOVE PROTECTION YOU CAN TRUST

LAVENDER\* Exam Gloves are tested extensively to ensure they will protect users in a wide range of situations. They are an ideal choice when expected fluid exposure and abrasion potential are low to moderate. LAVENDER\* Exam Gloves also:

- Meet or exceed ASTM test standards for nitrile exam gloves<sup>1</sup>
- Pass ASTM test standards for viral penetration by blood-borne pathogens<sup>2</sup>
- Pass ISO standard for primary skin irritation and sensitivity<sup>3</sup>
- Tested against common healthcare chemicals including:<sup>4</sup>
  - Glutaraldehyde
  - Formaldehyde
  - Povidone Iodine
  - Quaternary Detergent

Tell Your Halyard Sales Representative you want to replace your facility's vinyl and latex gloves with the protection, performance, and comfort of LAVENDER\* Nitrile Exam Gloves. And Relax!

### COMFORT YOU CAN FEEL - AT A MORE AFFORDABLE PRICE

In a use test, over 85% of healthcare professionals significantly preferred Halyard's LAVENDER\* Nitrile Gloves over two leading "stretch" vinyl exam gloves. Additionally, these healthcare professionals also preferred LAVENDER\* Nitrile Gloves for tactile sensitivity, easier finger and hand movement, less hand fatigue, softness, coolness, and comfort. More comfort leads to greater compliance, which means better protection for staff and patients.



#### REASONS TO RELAX WITH LAVENDER\* GLOVES

- Superior durability and comfort compared to vinyl
- Avoids natural rubber latex allergies
- Affordable price



# LAVENDER\* NITRILE EXAM GLOVES

5 boxes of 100 count Exam Gloves = 2 boxes of 250 count LAVENDER\* Exam Gloves

**60% less storage space required with 250 count box**

Compared to standard 100 count boxes, 250 count LAVENDER\* Exam Gloves saves.

## SUSTAINABILITY SAVINGS:

- 60% reduction in storage space



## HALYARD\* LAVENDER\* NITRILE EXAM GLOVES ARE DESIGNED FOR A WIDE RANGE OF TASKS.

- Higher count per box saves space and waste
- Powder-free
- Ambidextrous
- Beaded cuffs
- Non-sterile
- Textured fingertips



## HALYARD Advantage\*

KNOWLEDGE NETWORK\* Accredited Education  
 In-Service Training and Technical Support  
 Credentialed Sales Representatives  
 Tools & Best Practices  
 Clinical Research  
 Commitment to Excellence

For more information, please visit:

[www.halyardhealth.com](http://www.halyardhealth.com)

Call 1-844-HALYARD (1-844-425-9273) in the United States and Canada.

1 ASTM D6319 Standard Specification for Nitrile Examination Gloves for Medical Application  
 2 ISO-10993-10 PRIMARY Skin Irritation & Sensitization  
 3 ASTM F739 Standard Test Method for Permeation of Liquids and Gases through Protective Clothing Materials under Conditions of Continuous Contact  
 4 ASTM F1671 Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens Using Phi-X174 Bacteriophage Penetration as a Test System

## HALYARD\* LAVENDER\* Nitrile Exam Gloves

Item	Description	Size	Packaging
52816	LAVENDER* Nitrile Powder-Free Exam Gloves	X-Small	250 eaches/box 10 boxes/case
52817	LAVENDER* Nitrile Powder-Free Exam Gloves	Small	250 eaches/box 10 boxes/case
52818	LAVENDER* Nitrile Powder-Free Exam Gloves	Medium	250 eaches/box 10 boxes/case
52819	LAVENDER* Nitrile Powder-Free Exam Gloves	Large	250 eaches/box 10 boxes/case
52820	LAVENDER* Nitrile Powder-Free Exam Gloves	X-Large	230 eaches/box 10 boxes/case

## Product Specifications

Gauge Thickness Measurements	MM	MIL
Middle Finger:	.07	3.5
Palm:	.05	2.8
Cuff:	.04	2.4
Average Length	242mm	(9.5")

## Physical Properties

### Before Aging

Tensile Strength:	23 MPa
Ultimate Elongation:	600%

### After Aging

Tensile Strength:	24 MPa
Ultimate Elongation:	550%

## Quality Standards

Exceeds current ASTM Standards for critical defects, tensile strength, and puncture resistance.

Passes primary skin irritation testing in accordance with ISO 10993-10(2010)

Manufactured in accordance with Quality System ISO 9001.

## Barrier Properties Breakthrough Time - ASTM F739

Glutaraldehyde 4%	>480 mins
Formaldehyde 10%	>480 mins
Povidone Iodine 10%	>480 mins
Quaternary Detergent	>480 mins

## AQL - ASTM D5151

Critical Defects Level	<1.0 AQL <sup>†</sup>
------------------------	-----------------------

<sup>†</sup> Acceptable Quality Level